

Instrument	Resist	Prebake	Exposure Time, PEB	Development
AS200	OiR 620-7i	90°C, 60 sec.	0.17, 115°C, 60 sec.	726MIF, 60 sec.
AS200	OiR 897-12i	90°C, 60 sec.	0.26, 115°C, 90 sec.	726MIF, 60 sec.
AS200	SPR 700-1.2	95°C, 60 sec.	0.26, 115°C, 60 sec.	726MIF, 60 sec.
AS200	SPR 955CM-0.9	90°C, 90 sec.	0.21, 120°C, 90 sec.	726MIF, 60 sec.
AS200	SPR 955CM-2.1	90°C, 90 sec.	0.3, 120°C, 90 sec.	726MIF, 60 sec.
AS200	SPR 220-3.0	115°C, 90 sec.	0.26, 115°C, 90 sec.	726MIF, 60 sec.
AS200	SPR 220-7.0	115°C, 90 sec.	0.43, 115°C, 90 sec.	726MIF, 90 sec.
AS200	AZ P4903	115°C, 90 sec.	(wait 45 min.) 8.2	AZ 421K, 3 min.
GCA 5X	S1805	115°C, 45 sec.	0.2, (115°C, 60 sec.)	726MIF, 60 sec.
GCA 5X	S1813	115°C, 60 sec.	0.35, (115°C, 60 sec.)	726MIF, 60 sec.
GCA 5X	S1818	115°C, 60 sec.	0.45, (115°C, 60 sec.)	726MIF, 60 sec.
GCA 5X	S1827	115°C, 90 sec.	0.6, (115°C, 60 sec.)	726MIF, 60 sec.
GCA 5X	SPR 220-3.0	115°C, 90 sec.	0.65, 115°C, 90 sec.	726MIF, 60 sec.
GCA 5X	SPR 220-7.0	115°C, 90 sec.	.09, 115°C, 90 sec.	726MIF, 90 sec.
GCA 5X	AZ P4903	115°C, 90 sec.	(wait 45 min.) 2.5	AZ 421K, 3 min.
Contact Aligners	S1805	115°C, 45 sec.	1.6	726MIF, 60 sec.
Contact Aligners	S1813	115°C, 60 sec.	2.5	726MIF, 60 sec.
Contact Aligners	S1818	115°C, 60 sec.	3.2	726MIF, 60 sec.
Contact Aligners	S1827	115°C, 90 sec.	5.2	726MIF, 60 sec.
Contact Aligners	AZ P4903	115°C, 90 sec.	(wait 45 min.) 30	AZ 421K, 3 min.