



Processing Conditions

Prebake: 4 minutes @ 170°C
Postbake: 4 minutes @ 170° C
Develop: 10 minutes in 300 MIF
Rinse: DI water
Dose: ~1000 μ C/cm²